

Technical datasheet

**Cold mix Emulsion with Aggregate Mixture
(< 6mm, cold mix 7-8%), Stock No: GD-2023-101**

Composition

- | | | |
|----------|---|------|
| 1. P-400 | : | 1% |
| 2. P-591 | : | 0.1% |

Technical Analysis

- | | | |
|---|---|----------------|
| 1. Residue on 600 microns | : | 0.05 max. |
| 2. Viscosity @ 25°C | : | 50-300 |
| 3. Coagulation of emulsion at low temperature | : | NIL |
| 4. Storage Stability | : | 1.0 |
| 5. Particle Charge | : | +ve |
| 6. Coating ability and water resistance | : | Good |
| 7. Miscibility with water (coagulation) | : | No Coagulation |
| 8. Penetration test | : | 60-150 |

The following test was carried out for assessment of the quality of maintenance mixes

- ☐ Water resistance test
- ☐ Workability test
- ☐ Binder content
- ☐ Bond test

Main Inspect Verifier : Manager QC

Note:

- All the parameters of Cold- mix Emulsion are according to IS: 8887
- Product Specification is subject to amendment and may change over time