



Technical datasheet

GD-140, (50% solid bitumen in xylene)

Stock No: GD-2023-102

Batch-1

Technical Analysis

1. Product Name	:	GD-140
2. Stock No.	:	GD-2024-102
3. Solvent	:	Xylene
4. Solvent (%)	:	50%
5. Solid Content	:	50%
6. Appearance	:	Smooth Liquid
7. Finish	:	Glossy
8. Softening Point of Bitumen (approx.)	:	138.9°C
9. Viscosity @ 30°C	:	69 sec
10. Specific Gravity @ 30°C	:	0.98
11. Surface dry	:	8-10 mins.
12. Complete Dry	:	20 mins.

Main Inspect Verifier : Manager QC

Note:

- All the parameters of GD-140 are according to customer requirement
- Product Specification is subject to amendment and may change over time



FACTORY

467/3, Naigaon Road, Shinde,
Nashik - 422 102.



OFFICE

Pritam Complex, Amrutdham,
Near East End Hotel, Hanuman Nagar,
Panchavati, Nashik - 422 003.



GSTIN : 27AAVFG1857A1ZA

goldenexusllp@gmail.com